



2157-3

**Workshop on Principles and Design of Strongly Correlated Electronic
Systems**

2 - 13 August 2010

**Landau-Level Spectroscopy of Helical Dirac Fermions in a Topological Insulator
Bi₂Se₃**

Tetsuo HANAGURI

Magnetic Materials Lab.

RIKEN Advanced Science Institute, 2-1 Hirosawa

Wako 351-0198

Saitama

JAPAN

Landau-level spectroscopy of helical Dirac fermions in a topological insulator Bi_2Se_3



RIKEN

Tetsuo Hanaguri

RIKEN **M. Kawamura**

U. Tokyo/RIKEN **H. Takagi**

Tokyo Inst. Tech. **K. Igarashi**

T. Sasagawa

Why STM?

Search for unusual electronic states

Breaking down
"boring" materials

Detection



- quantum structure
- interface
- impurity
- ...

Microscopic properties

**Electron
Systems**

Macroscopic properties

- superconductivity
- magnetism
- ...


Emergence



Building up
"boring" electrons

Why STM is powerful?

- **Atomic spatial resolution**
 - ~ 0.1 nm laterally, \sim pm vertically
 - local information is available
- **Momentum-space accessible**
 - FT-STS with large field of views
- **Very high energy resolution**
 - as high as $\sim \mu\text{eV}$
- **Workable under extreme/variable environments**
 - high fields, low temperature, UHV...
 - can be used to study phase transitions





Powerful tool to
explore the
electronic states

Target specifications of spectroscopic STM

- **Ultra-high vacuum $\sim 10^{-10}$ Torr**
 - to keep the surface clean for a long time
- **High magnetic field > 10 T**
 - to control the spin, orbital and phase
- **Very-low temperature < 1 K**
 - to reduce the thermal broadening ($1 \text{ K} \sim 0.1 \text{ meV}$)
 - Mott gap : $\sim \text{eV}$
 - SC gap (HTSC) : $\sim 10 \text{ meV}$
 - Impurity resonances : $\sim 1 \text{ meV}$
 - Zeeman energy : $\sim 0.06 \text{ meV/T}$
- **Variable temperature**
- **Long-term stability**
 - 256×256 pts, 2 sec/pt, \rightarrow **36 hours**

RIKEN multi-extreme STM (based on UNISOKU USM-1300)

T. Hanaguri, J. Phys.: Conf. Ser. 51,514 (2006).




- Very-low and variable temp. (400 mK - 60 K)
- High field (11 T), UHV ($\sim 10^{-10}$ Torr)
- *In-situ* tip/sample exchange (resonant freq. 5.5 kHz)
- Atomically controlled tip sharpening by FIM
- Noise levels (1 kHz BW) < 0.5 pm, 1 pA

Performance tests

NbSe₂ $T_c = 7.1$ K, $T_{CDW} = 29$ K




$T \sim 1.5$ K




10 nm × 10 nm, +50 mV/0.1 nA

$T \sim 400$ mK



Energy resolution is thermally limited.

Momentum-resolved Landau level spectroscopy in a topological insulator Bi_2Se_3



Topological insulators


X. -L. Qi and S. -C. Zhang, *Physics Today* 63, 33 (2010).
M. Z. Hasan and C. L. Kane, arXiv:1002.3895v1.

(Band) insulators with
robust gapless edge or surface state


How can they become true?

→ Band structure with specific "topology"

ex. Quantum Hall state



Gapless edge-state



Time-reversal symmetry is broken.

Topological insulators


X. -L. Qi and S. -C. Zhang, *Physics Today* 63, 33 (2010).
M. Z. Hasan and C. L. Kane, arXiv:1002.3895v1.

(Band) insulators with
robust gapless edge or surface state


How can they become true?

→ Band structure with specific "topology"

Topological insulator (Quantum Spin Hall insulator)



Gapless edge-state




Time-reversal symmetry is preserved.

Dirac cone on the surface

3D topological insulator \rightarrow Gapless surface state

Helical Dirac fermions at the surface



No spin
degeneracy

Odd # of cones centered
at time-reversal invariant
momenta (TRIM)

Doubly
degenerate

Always come in pairs

Dirac cones in solid states



- **Graphene** *A. H. Castro Neto et al., Rev. Mod. Phys. 81, 109 (2009).*
- **Organic conductor** *N. Tajima et al., EPL 80, 47002 (2007).*
- **d-wave SC** *A. V. Balatsky, I. Vekhter, and J.-X. Zhu, Rev. Mod. Phys. 78, 373 (2006).*

Experimental verifications

- 2D : HgTe quantum well



B. A. Bernevig, T. L. Hughes, S.-C. Zhang, *Science* **314**, 1757 (2006).
 M. König *et al.*, *Science* **318**, 766 (2007).

- 3D : Bi-Sb





D. Hsieh *et al.*,
Nature **452**, 970 (2008).

- Bi_2Se_3 H. Zhang *et al.*, *Nature Phys.* **5**, 438 (2009).



Y. Xia *et al.*, *Nature Phys.* **5**, 398 (2009).

- Bi_2Te_3




Y. L. Chen, *et al.* *Science* **325**, 178 (2009).

What unusual things happen?

- Helical spin structure : **Suppressed back scattering**




Bi-Sb



P. Roushan *et al.*,
Nature **460**, 1106 (2009).

Bi₂Te₃



Z. Alpichshev *et al.*,
PRL **104**, 016401 (2010).

- Massless Dirac dispersion: **Unusual Landau levels**

Conventional electron :
$$E_n = E_0 + \frac{e\hbar B}{m} \left(n + \frac{1}{2} \right)$$

Dirac fermion :
$$E_n = E_0 + \text{sgn}(n)v\sqrt{2e\hbar|n|B}$$


If $n = 0$, LL is B independent.

STM/STS on Bi_2Se_3


T. Hanaguri *et al.*, arXiv:1003.0100. (PRB-RC in press.)

X'tals grown by Igarashi & Sasagawa (TIT)

$T \sim 1.5$ K



30 nm \times 30 nm, -100 mV/0.1 nA



cf. S. Urazhdin *et al.*, Phys. Rev. B **66**, 161306(R) (2002); S. Urazhdin *et al.*, *ibid.* **69**, 085313 (2004).

Search for QPI in Bi_2Se_3

T. Hanaguri *et al.*, arXiv:1003.0100. (PRB-RC *in press.*)




QPI is very weak
in single,
isotropic and
helical Dirac cone.

$g(r, E) / \langle g(r, E) \rangle$ $T \sim 1.5$ K

1.4



0.6





30 nm \times 30 nm, +100 mV/0.1 nA

Sb

$g / \langle g \rangle$



0.6 1.4



K. K. Gomes *et al.*,
arXiv:0909.0921.

Landau level spectroscopy in Bi_2Se_3

T. Hanaguri *et al.*, arXiv:1003.0100. (PRB-RC *in press.*)
See also, P. Cheng *et al.*, arXiv:1001.3220.



- Field-independent Landau level with $n = 0$
- E_n is sub-linear in n

Scaling analysis

T. Hanaguri *et al.*, arXiv:1003.0100. (PRB-RC *in press.*)


$$E_n = E_0 + \text{sgn}(n)v\sqrt{2e\hbar|n|B}$$

Bohr-Sommerfeld condition

$$S_n = (n + \gamma)\frac{2\pi eB}{\hbar} \approx \pi k_n^2$$

$\gamma = 0$ for Dirac fermion


$$k_n = \sqrt{\frac{2e|n|B}{\hbar}}$$




New momentum-resolved spectroscopy using STM

Other unusual features

T. Hanaguri *et al.*, arXiv:1003.0100. (PRB-RC *in press.*)





- Missing $n < 0$ LLs
 - coupling with bulk band?
- Enhanced amplitude near E_F



- E -dependent QP lifetime

Anomalous fine features near E_F



T. Hanaguri *et al.*, arXiv:1003.0100. (PRB-RC *in press.*)



- Fine structures appear near E_F

Anomalous fine features near E_F


T. Hanaguri *et al.*, arXiv:1003.0100. (PRB-RC *in press.*)




- Fine structures shift in the same manner as LLs

Anomalous fine features near E_F

T. Hanaguri *et al.*, arXiv:1003.0100. (PRB-RC *in press.*)



Anomalous large amplitude magneto-fingerprint effect



J. G. Checkelsky *et al.*,
PRL 103, 246601 (2009).

- Amplitude enhances suddenly $|E| < \sim 20$ mV

Summary

- **Stable STM** which can be operated under combined extreme conditions has been successfully installed.
- **Helical Dirac fermions** at the surface of a topological insulator Bi_2Se_3 has been studied using STM/STS in a magnetic field.
- **Landau levels** were identified clearly. We developed a new analysis scheme which enables us to determine the band dispersion accurately.
- **Anomalous fine structures** were found near E_F .

*Spectroscopic basis for understanding
magneto-transport and other properties
of topological insulators*

Issues

- Magnetic impurity
- How to reduce carriers?